

Technical Bulletin - Instructions

Achilles Structural Lines Film

Backing material: Sheet lamination: - paper 115 g/m 2 to card 450 g/m 2

gloss- or silk-coated printing substrates - uncoated qualities only after consultation - relative paper moisture approx. 50 %

- here nearly any paper quality is possible (max. 380 g/m²) Composite lamination:

depending on the intended purpose

hologram paper from 78 g/m²

Composite surface: matt side to the outside

Visual appearance: - matt

- it is always the non-matt side which is laminated as backing material.

The matt surface is always outside.

Formats: - max. sheet width 1010 mm

- optimum sheet widths = 100 cm und 70 cm

- please ask about other widths

Printing inks: Inks must be suitable for lamination: consult ink manufacturer if necessary; the inks must be dried

through completely and resistant to solvents and alkaline solutions as per DIN 16524.

Surface tension should be >35mN/m. Possible changes in ink must be taken into account in the prepress or printing phase; sample lamination is advisable. Metal pigment inks must be coordinated

in particular to the lamination process; consult the ink manufacturer.

Printing aids: Only little powder, remove powder preferably before finishing. Use starch powder with adapted

grain size as powder. Do not add scouring protection paste, wax and silicone to the inks. Minimise moisture level in neutral range. Primers must withstand sellotape and be migration-proof, dried through and suitable for gluing: apply with minimum force. Primers are not suitable for

subsequent fold enamelling and HF drying.

Positioning and 10 mm trimming edge all round, unprinted and unvarnished.

production edges: Please enclose dummy sheet indicating details of the finished format and trimming.

- varnishing using the screen printing method Processing:

- structure embossing

punching, creasing, folding, grooving
gluing (job-oriented test absolutely necessarily)

applying stickers (resistant to sellotape)

embossed film printing (looks visually different with Matt OPP film)

bookbinding cover production

- The processing method (e.g. creasing, grooving, folding) is to be taken into

account when selecting the backing material.

We generally recommend a processing test with a printer sheet!

- heat-sealing with foil (e.g. pocket sealing) not possible:

Advice for shipping: - Please make sure that products used with ASM films are not open to vibration or movement

whilst being shipped or transported.

Please...

...send a detailed specification with your order together with a dummy sheet indicating the scope of our work. Please also inform us about subsequent processing steps so that we can use the right materials for your purpose. It is also important to inform us of the required delivery address if this is not the same as the purchaser's address. Please inform us in advance if the processed quantity differs from the quantity supplied to us, as otherwise all supplied sheets will be processed and charged. Compliance with these points will result in swift, uncomplicated processing of your order without the need for any queries. Coordination of all production processes and materials guarantees optimum production results. Profit from our experience, know-how and possibilities. Ask and inform us in plenty of time, we will be glad to advise you.

The details contained in this bulletin comply with the current state of our know-how; they do not constitute any extension of the guaranteed services stipulated in our delivery conditions and are in particular no warranted properties. This information bulletin can only provide unbinding advice with regard to differences in printing substrates and working conditions. Before circulation printing begins, it is important for the printers to check by suitable means whether the materials are appropriate for the intended purpose